



Chemical Resistance Guidelines for Liqui-Cel®, SuperPhobic®,
MiniModule®, and MicroModule® Contactors

MEMBRANA
A POLYPORE Company

www.liqui-cel.com



CHEMICAL RESISTANCE TABLE

The Chemical Resistance Table below is an informational guide for the use of various chemicals with components used in Membrana Membrane Contactors. The contents of this table are the general chemical resistance characteristics of the raw materials for the contactor components. The table is a general guide only and should not be considered as a substitute for testing under your specific conditions.

Chemical Resistance Classification	
S	Satisfactory. No or very little chemical influence on performance
L	Limited Resistance. Exposure time must be limited to maintain adequate performance
U	Unsatisfactory. Adequate performance not possible with this chemical
	Blank. Chemical is Untested

Chemical Resistance Summary

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Water & Aqueous Solutions	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Bases	S	U	S	S	S	S	S	S	S	L	L	L	S	S
Acids-Dilute	L	L	S	S	S		S	S	S	U	S	L	S	S
Acids-Strong	U	U	L	L	L		U	S	U	U	L	L	S	L
Halogens	U	U	U	U	U		U	S	U	U	L	L	S	U
Aliphatic Hydrocarbons	S	L	L	L	L		U	S	L	S	L	S	S	U
Alicyclic Hydrocarbons	S	L	L	L	L		U	L	U	L	L	S	S	U
Aromatic Hydrocarbons	L	L	L	L	L		U	S	U	S	U	S	S	U
Heterocyclic Compounds	L	U	L	L	L			L	U	L	L	L	S	U
Amines	L	U	L	L	L		U	U	U	L	U	U	S	L
Alcohols	S	U	S	S	S	S	U	S	L	S	S	L	S	S
Glycols & Glycerols	S	U	S	S	S		L	S	S	S	L	L	S	S
Aldehydes	L	U	L	L	L		U	U	L	S	L	L	S	L
Ketones	L	U	S	S	S		U	U	U	S	U	U	S	L
Anhydrides	U	U	S	S	S			U	U	S	U	U	S	
Halogenated Hydrocarbons	L	U	U	U	U		U	L	U	L	U	L	L	U
Esters	L	U	S	L	L		U	L	U	S	U	U	S	L
Phenolics	L	L	S	S	S		U	L	L	U	U	U	S	L

Chemical Resistance Table

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Acetaldehyde	U	U	L	L	L	S	U	U	U	S	L	U	S	L
Acetic Acid (10%)	L	L	S	S	S	S	L	S	U	U	S	L	S	S
Acetic Acid (Glacial)	U	U	S	S	S	S	U	L	U	S	S	U	S	L
Acetic Anhydride	U	U	S	S	S	S	U	U	U	S	U	U	S	L
Acetone	L	U	S	S	S	S	U	U	U	S	U	U	S	S
Acetonitrile	U	U	S	S	L	S		L	U	S	U	U	S	S
Acetophenone	U	U	S	S	L		U	U	U	S	U	U	S	S
Acetyl Chloride	U	U	L	U		S	U	L	L	S		S	S	U
Acrylic Acid 140	U	U	S	L				S				U	S	L
Aluminum Chloride (10%)	S	L	S	S	S	U	S	S	S	U	S	S	S	S
Aluminum Sulphate	S	L	S	S	S	L	S	S	S	S	S	S	S	S
Ammonium Hydroxide (35%)	L	U	S	S	S	S	S	S	S	S	S	L	S	S

PO = Polyolefin in SuperPhobic Products
 PC=Polycarbonate
 PU=Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Ammonium Sulphate (50%)	S	L	S	S	S	S	S	S	S	S	S	S	S	S
Amyl Acetate	L	U	S	L	L	S	U	L	U	S	U	U	S	S
Amyl Alcohol	S	U	S	L	L	S	S	L	S	S	S	L	S	S
Aniline	U	U	S	S	L	S	U	L	L	S	U	S	S	L
Antimony Trichloride (10%)	S	S	S	S		U	S		S	U	S	S	S	
Aqua Regia	U	U	U	U	U	U	U	L	L	U	U	L	S	L
Arsenic Acid	L	L	S	S	S	S	S	S	S	L	S	S	S	S
ASTM OIL #1	S	L	S	S								S	S	U
ASTM OIL #2	S	L	S	L								S	S	U
ASTM OIL #3	S	L	S	L								S	S	U
Barium Chloride	S	S	S	S		S	S	S	S	S	S	S	S	S
Benzaldehyde	U	U	S	U	L	S	S	L	U	S	U	U	S	S
Benzene	S	U	L	U	U	S	U	S	L	S	U	S	S	U
Benzyl Alcohol	U	U	S	S	S		U	S	L	U	U	S	S	L
Benzyl Chloride	U	U	L	L		S	U	S		S	U	S	S	U
Boric Acid	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Bromine	U	U	U	U	U	U	U	S	L	U	L	S	S	U
Butyl Acetate	L	U	S	L	L	S	U	L	U	S	U	U	S	L
Butyl Alcohol (Butanol)	S	U	S	S	S	S	U	S	L	S	S	L	S	L
Butyl Amine	L	U		L			U	U	U	S	U	U	S	U
Butyric Acid	U	U	L	S	U	S	U	S	S	L	U	S	S	L
Butyl Chloride	S	U	U	U	L		U	S	L	S	S	L	S	
Calcium Chloride	S	S	S	S	S	S	S	S	L	S		S	S	S
Carbon Disulphide	S	U	U	U	U	S	U	L	U			S	S	U
Carbon Tetrachloride	S	U	U	U	U	S	U	S	U	U	U	S	L	U
Castor Oil	S	S	S	S			S	S				S	S	L
Cello-Solve Glycol Ether	U	U										S	S	
Cello-Solve Acetate	U	U	S	S	S		U	S	L	S	L	U	S	L
Chloroacetic Acid	U	U	S	L	S	S		U	S	U	U	U	S	L
Chlorobenzene	U	U	L	U	U	S	U	S	U	U	U	S	S	U
Chlorine Dioxide	U	U			U			S				S	S	L
Chlorine Gas	L	U	L	U	L	S		S	U	U	L	S	S	U
Chlorine (Water)	L	L	L	U	U	L	U	S	S	L	L	S	S	L
Chloroform	U	U	L	U	U	S	U	L	U	S	U	S	S	U
Chlorosulphuric Acid	U	U	U	U								U	S	
Chrome Plating Solutions	U	U	S	L								S	S	L
Chromic Acid	U	U	S	L	L	S	L	L	S	U	U	S	S	L
Citric Acid (10%)	S	S	S	S	S	S	S	S	S	S	S	S	S	S
COD Liver Oil	L	L	S	S								S	S	S
Copper Sulphate	S	S	S	S	S	S	S	S	S	U	S	S	S	S
Cottonseed Oil	S	S	S	S				S	S	S		S	S	L
Cresols	U	U	L	L	U	S	U	S	U	U	U	S	S	U
Cyclohexane	S	S	L	L	U	S	U	S	U	S	S	S	S	U
Cyclohexanol	S	L	S	L	S		U	S	U	L	L	S	S	U
Cyclohexanone	S	L	S	U	L	S	U	L	U	S	U	U	S	L
Decahydronaphthalene	L	U	L	U	L				S	S	S	S	S	U
Diesel	S	L	L	L		S		S	S	S	S	S	S	U
Diethylamine	U	U	L	L	L	S	U	L	U	S		S	S	L
Diethylene Glycol	S	U	S	S	S	S	S	S	L	S	L	S	S	S
Diethyl Ether	L	U	L	L	U	S	U	S	U	S	U	U	S	U

PO = Polyolefin in SuperPhobic Products
 PC=Polycarbonate
 PU=Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Dimethyl Formamide	U	U	S	S	S	S	U	U	U	S	U	U	S	L
Dimethyl Hydrazine	U	U	S	S								U	S	
Dimethylamine	U	U	S	L				L			U	U	S	
Diocetyl Phthalate	S		S	S	S			L	U	S		L	S	
Dioxane	U	U	S	U	L		U	U	U	L	U	U	S	L
Ethyl Acetate	L	U	S	L	L	S	U	U	U	S	U	U	S	L
Ethyl Alcohol (Ethanol)	S	U	S	S	S	S	S	S	L	S	S	L	S	S
Ethyl Chloride	U	L	U	U	L	S	U	S	U	S	U	L	S	L
Ethylamine	U	U	L	L								U	S	
Ethylene Bromide	L	U	L	U		S	U		U		U	U	S	
Ethylene Dichloride	U	U	L	U		S		S	U	S	U	L	S	L
Ethylene Glycol	S	U	S	S	S	S	S	S	S	S	S	L	S	S
Ferric Chloride	S	S	S	S	S	U	S	S	S	S	S	S	S	S
Fluorine (Gas)	U	U	U	U	L	S	S	L	U	U	L	L	S	U
Fluoroboric Acid	L	U	S	L				S	S	U		S	S	S
Fluorosilicic Acid	L		S	S		S	S	S	U	U	S	S	S	
Formaldehyde (40%)	S	U	S	S	S	S	S	L	S	S	S	S	S	L
Formic Acid (90%)	U	U	S	S	S	S	U	S	S	U	S	L	S	88% S
Freon 11 Refrigerant	S	U	L	S		S	U	S	S	U		S	L	
Freon 113 Refrigerant	S		L	U			S		S		S	S	L	
Freon 115 Refrigerant	S		L	U								S	L	
Freon 12 Refrigerant	S	L	L	S		S	S	S	S	S	U	L	L	
Freon 13 Refrigerant	S		S									S	L	
Freon 21 Refrigerant	S		S									U	S	
Freon 22 Refrigerant	S	U	S	L		S	U	S	S	S		U	S	
Freon 32 Refrigerant	S		S									U	L	
Furfural	S		L	U		S	U	L	U	S	U	U	S	L
Gasoline	S	U	L	U	L	S	U	S	S	S	S	S	S	U
Glycerol	S	S	S	S	S	S		S	S	S	S	S	S	S
Hexane	S	L	L	L	L		U	S	S	S	L	S	S	U
Hydrazine	L	L	S	U	U	S		S	U	U	U	U	S	S
Hydrobromic Acid (50%)	L	U	S	L	S	U	S	S	S	U	L	S	S	
Hydrochloric Acid (10%)	S	U	S	S	S	U	S	S	S	U	S	S	S	S
Hydrochloric Acid (36%)	U	U	S	S	S	U	S	S	S	U	U	S	S	Hot - U
Hydrofluoric Acid (40%)	U	U	S	S	S	S	L	S	S	U	U	S	S	U
Hydrogen Peroxide (35%)	U	U	S	L	S	S	S	S	S	To 5% L	S	S	S	S
Hydrogen Peroxide (87%)	U	U	S	U	S	S	S	L	S	U	S	S	S	
Hydrogen Sulphide (Gas)	S	L	S	S		S		S	S	L		S	S	S
Iso-Octane	S	U	S	U				S	S	S	S	S	S	U
Iso-Propyl Alcohol	S	L	S	S	S	S		S	L	U	S	S	S	S
Lactic Acid	S	S	S	S	S	S	U	L	S	S	S	S	S	S
Lead Acetate (10%)	S	U	S	S	S	S	S	S	S	S	S	L	S	S
Linseed Oil	S	L	S	S	S	S		S	S	S	S	S	S	L
Lubricating Oil	S	L	S	S		U		S	S	S	S	S	S	U
Magnesium Chloride	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Methyl Bromide	U	U	U	U		S	U	S	U	S		S	S	U
Methyl Ethyl Ketone	U	U	S	S	L	S	U	U	U	S	U	U	S	S
Methyl Alcohol (Methanol)	S	U	S	S	S	S	U	S	S	S	S	U	S	S

PO = Polyolefin in SuperPhobic Products
 PC=Polycarbonate
 PU=Polyurethane

PE = Polyethylene
 PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Methylene Dichloride	U	U	L	L		S						L	S	
Molasses	S	S	S	S		S	S	S	S	S		S	S	
Monoethanolamine	L	U	L	L				U	U	S		U	S	
N-Propyl Alcohol	S	U	S	S		L		S				S	S	S
Nickel Chloride	S	S	S	S	S	L	S	S	S	L	S	S	S	S
Nitric Acid (10%)	L	L		S	S	S	S	S	U	U	S	S	S	L
Nitric Acid (70%)	U	U	L	L	L	S	L	L	U	U	L	U	S	U
Nitrobenzene	U	U	L	L	L	S	U	L	U	S	U	L	S	U
Nitromethane	U	U	L	L	L	S	U	S	S	S	U	U	S	L
Nitropropane	L	U	L	L			U	U				U	S	L
Oleic Acid	S	L	S	S		S	U	S	L	L	S	S	S	U
Olive Oil	S	S	S	S		S	S	S	L	S	S	S	S	L
Oxalic Acid	S	L	S	S	S	S	S	L	S	S	S	S	S	S
Ozone (Gas)	L	L	L	U	S	S	S	S	S	U	S	S	S	S
Paraffin Oil	S	L	S	S	L	S	S	S	S	S	S	S	S	
Perchloroethylene	S	U	L	U	U	S	U	S	L	L	U	S	S	U
Peroxymono-sulphuric Acid	U	U			S	S						S		
Phenol	U	U	S	L	U	S	U	L	L	U	U	S	S	U
Phosphoric Acid (85%)	L	L	S	S	S	U	L	S	S	S	S	S	S	S
Picric Acid	U	U	S	U	S	S	S	L	U	L	U	S	S	L
Plating Solutions (<i>not chrome</i>)	L	L	S	S				S				S	S	S
Potassium Cyanide	S	S	S	S	S	S	S	S	S	S		S	S	S
Potassium Fluoride	S	S	S	S		S	S	S				S	S	
Potassium Hydroxide (50%)	S	U	S	S	S	S	S	U	S	L	U	L	S	S
Potassium Permanganate	U	U	S	S	S	S	S	S	S	U	S	S	S	
Potassium Sulphate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Propionic Acid	S	L	S	S	L		U	S	L	U	U	S	S	
Pyridine	U	U	L	S	L	S	U	U	U	L	U	U	S	L
Rapeseed Oil	L	L	L	U		S						S	S	S
Silicone Fluids	L	S	S	S	S	S	U	S	S	S	S	S	S	
Silver Nitrate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Borate	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Carbonate	S	S	S	S	S	S	S	S	S	S	S	S	S	
Sodium Chloride	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Sodium Chlorite	S	S	S	S			S	S				S	S	
Sodium Cyanide	S	S	S	S	S	S	S	S	S	S		L	S	S
Sodium Hydroxide (10%)	S	U	S	S	S	S	S	L	S	S	S	L	S	S
Sodium Hydroxide (60%)	S	U	S	S	S	S	S	U	S	L	U	L	S	S
Sodium Hypochlorite (20%)	L	U	L	L	S	L	S	S	S	U	L	L	S	L
Sodium Nitrate	S	S	S	S	S	S	S	S	S	S	U	S	S	S
Sour Oil	S		L					L				L	S	U
Stannic Chloride	S	S	S	S		U		S	S	S	S	S	S	S
Styrene	L	U	L	L	L	S		S	U	S	U	S	S	U
Sulfamic Acid	L	U					S					L	S	
Sulphur Dioxide (Gas)	S	L	S	S	S	S	U	S	S	L	S	S	S	S
Sulphuric Acid (10%)	S	L	S	S	S	L	S	S	S	L	S	S	S	S
Sulphuric Acid (70%)	U	U	S	L	S	U	S	S	S	U	S	S	S	
Sulphuric Acid (96%)	U	U	S	L	L	U	S	S	U	U	U	L	S	U

PO = Polyolefin in SuperPhobic Products
PC=Polycarbonate
PU=Polyurethane

PE = Polyethylene
PP = Polypropylene

	POTTING/CASE			FIBER/CASE		HOUSINGS						O-RINGS/SEALS		
	Epoxy	PU	PE	PP	PO	316LSS	ABS	PVDF	PVC	NYLON	PC	Viton®	Kalrez®	EPDM
Sulphuric Acid (Fuming)	U	U	L	U	U	U		U	U	U	U	L	S	
Tetrachloroethane	S	U	L	L		S	U	S	L	L		S	S	U
Tetrahydrofurane	U	U	L	L	L	S	U	U	U	S	U	U	S	L
Tetrahydro-naphthalene	S	U	L	U								S	S	
Thionyl Chloride	U		U	U	U		U	U	U	U	U	U	S	L
Titanium Tetrachloride	S	S	L	L				S				S	S	U
Toluene	L	U	L	U	L	S	U	S	U	S	U	S	S	U
Transformer Oil	S	S	S	L			S					S	S	U
Trichloroacetic Acid	L	U	S	S	S	L		L	L	L	U	L	S	L
Trichloroethane	L	U	U	U	U	S	U	S	L	L	U	S	S	U
Trichloroethylene	L	U	U	U	U	S	U	S	U	L	U	L	S	U
Tricresyl Phosphate	S		S	S		S	U	U	U	S		S		S
Triethanolamine	S	U	S	L				L				U	S	L
Triethylamine	S	U	S	U		S	U	L	S	S		L	S	
Turpentine	L	U	L	L	L	S	U	S	U	S	U	S	S	U
Vegetable Oils	S	S	L	L		S	S	S	S	S		S	S	L
Vinyl Acetate	L	L	S	S		S	U	S	U			U	S	L
Vinyl Chloride	U	L	U			S	U	S	U	S		S	S	U
Water (Distilled)	S	S	S	S	S	S	S	S	S	S	S	S	S	S
Water (Sea)	S	S	S	S	S	S		S	S	S	S	S	S	
Wine	S	U	S	S		S	L	S	S	S	S	S	S	S
Xylene	L	U	L	U	L	S	U	S	U	S	U	S	S	U

PO = Polyolefin in SuperPhobic Products
 PC=Polycarbonate
 PU=Polyurethane

PE = Polyethylene
 PP = Polypropylene



This product is to be used only by persons familiar with its use. It must be maintained within the stated limitations. All sales are subject to Seller's terms and conditions. Purchaser assumes all responsibility for the suitability and fitness for use as well as for the protection of the environment and for health and safety involving this product. Seller reserves the right to modify this document without prior notice. Check with your representative to verify the latest update. To the best of our knowledge the information contained herein is accurate. However, neither Seller nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material and whether there is any infringement of patents, trademarks, or copyrights is the sole responsibility of the user. Users of any substance should satisfy themselves by independent investigation that the material can be used safely. We may have described certain hazards, but we cannot guarantee that these are the only hazards that exist.

Liqui-Cel, Celgard, SuperPhobic, MiniModule and MicroModule are registered trademarks of Membrana-Charlotte, A division of Celgard, LLC and nothing herein shall be construed as a recommendation or license to use any information that conflicts with any patent, trademark or copyright of Seller or others.

To insure you are evaluating the most current information on our products, please review the English versions of our literature on our website. The English documents are the correct documents to be referenced.

©2009 Membrana - Charlotte A Division of Celgard, LLC Chemical GD_Rev6_06-09

Membrana - Charlotte
 A Division of Celgard, LLC
 13800 South Lakes Drive
 Charlotte, North Carolina 28273
 USA
 Phone: (704) 587-8888
 Fax: (704) 587-8610

Membrana GmbH
 Oehder Strasse 28
 42289 Wuppertal
 22844 Norderstedt
 Germany
 Phone: + 49 202 6099 -658
 + 49 6126 2260 -41
 Fax : + 49 202 6099 -750

Japan Office
 Shinjuku Mitsui Building, 27F
 1-1, Nishishinjuku 2 -chome
 Shinjuku-ku, Tokyo 163-0427
 Japan

Phone: 81 3 5324 3361
 Fax: 81 3-5324 3369

MEMBRANA
 Underlining Performance

www.liqui-cel.com

A **POLYPORE** Company